

Trademark	Emsodur Acryl, Type V
Manufacturer	Emsodur AG Industriepark Vial 2 CH-7013 Domat/Ems Tel.: +41 81 632 80 11
Colour	transparent
Shape	irregular with sharp, angular edges and corners
Dimension	0.10-0.20mm 0.20-0.40mm 0.60-0.80mm 0.80-1.20mm 1.20-1.70mm
Storage stability	unlimited, when stored in a cool and dry place

Physical characteristics

Density	1.15 – 1.20 g/cm ³
Bulk density	0.55-0.65 kg/l (depending on size)
Hardness	46-54 Barcol 2.5 Mohs
Water absorption	<2.0% (23°C/50 % r.F. DIN 53472)

Chemical characteristics

Composition	Polymethylmetacrylate polymer
pH-value	4 – 8 (bei 250 g/l H ₂ O, 20°C)
Ash content	max. 0.5%

Thermic characteristics

Flash point	300°C
Thermic decomposition	136°C